

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 1 362 687 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
19.11.2003 Bulletin 2003/47

(51) Int Cl.7: B29C 59/00, B60R 21/20

(21) Application number: 03014875.3

(22) Date of filing: 25.06.1999

(84) Designated Contracting States:
DE ES FR GB IT SE

(72) Inventor: Nicholas, Antonios
Belle Mead, New Jersey 08502 (US)

(30) Priority: 25.06.1998 US 90622 P

(74) Representative: Schaumburg, Thoenes & Thurn
Postfach 86 07 48
81634 München (DE)

(62) Document number(s) of the earlier application(s) in
accordance with Art. 76 EPC:
99112282.1 / 0 967 066

(71) Applicant: TIP ENGINEERING GROUP, INC.
Farmington Hills, Michigan 48334 (US)

Remarks:

This application was filed on 30 - 06 - 2003 as a
divisional application to the application mentioned
under INID code 62.

(54) Process for manufacturing an automotive trim piece preweakened to form an air bag deployment opening

(57) A process for manufacturing a trim piece to provide a concealed deployment door and opening for an air bag in which a substrate panel is formed with one or more integral door panels having an interposed gap preformed between one or more door panels and the substrate panel, and one side of each door panel is integral

with the substrate panel structure to form a hinge. The substrate panel is overlain with one or more covering layers extending over the door panel or panels and opening. The covering layers can be preweakened along the gap in a correlated pattern, as by laser scoring.




FIG - 1

Description

Background of the Invention

[0001] This invention concerns the manufacture of trim pieces such as instrument panels and steering wheel covers which overlie air bag installations, and more particularly processes for manufacturing trim pieces which have air bag canisters installed behind the trim pieces which are preweakened to allow an inflating air bag to form a deployment opening by forcing a concealed door section of the trim piece to separate and swing out from the adjacent portion of the trim piece structure.

[0002] One or more hinged deployment door panels overlying the air bag have long been incorporated in such auto trim pieces, which are held closed by tabs or other elements and are then forced open by the inflating air bag when the air bag is deployed.

[0003] In recent years, so called "invisible seam" installations have been developed, in which the separate visibly delineated doors initially used have been eliminated, and a smooth overlying covering extends over the trim piece location whereat the air bag is mounted.

[0004] An opening is formed in the trim piece when the air bag is activated by the inflating air bag forcing itself through a section of the trim piece. This is accomplished by a preweakening of the trim piece at the air bag location to allow the pressure of the inflating air bag to cause a "door" tear in the trim piece to break free and hinge open along one side.

[0005] Trim pieces are often constructed in layers including a stiff substrate panel, and overlying skin and foam covering layers, or with a skin bonded to a substrate panel.

[0006] The substrate may be molded first, and the skin and foam added subsequently.

[0007] The preweakening has involved the formation of preweakening grooves in the trim piece and/or covering layers molded into the piece, or the formation of the grooves as by laser scoring of the trim piece or components thereof.

[0008] A separate door panel is often fit into an opening molded into the substrate panel, but this requires additional processing steps.

[0009] Cutting through a substrate panel to form the door has also been practiced, but this requires a powerful cutting apparatus to sever the relatively thick substrate, increases cycle time, and in the case of laser cutting, requires handling of the by-products generated by vaporizing of the substrate material.

[0010] It is the object of the present invention to provide a simplified method of manufacturing an automotive trim piece which is preweakened to form an invisible seam deployment door opening for air bags.

Summary of the Invention

[0011] The above object and other which will be understood upon a reading of the following specification and claims is achieved by a process in which a substrate panel is preformed with one or more deployment door panels, each integrally connected along one side to adjacent portions of the substrate panel, and with a gap spacing the unconnected door sides from the adjacent substrate sections. The connected side of the door panel functions as a hinge when the panel is contacted by the inflating air bag.

[0012] Bridging tabs may optionally be formed extending across the gap at one or more locations to stabilize the panel with respect to the rest of the substrate panel.

[0013] The one or more covering layers are later added or formed at the same time to overlie the substrate panel. The covering layers may also be cut or scored as by directing a laser beam or other scoring or cutting agent through and along the gap, and tracing along the path of the gap in a door pattern, to preweaken the covering layer in a pattern corresponding to the free, unhinged sides of the door sections.

Description of the Drawing Figures

[0014]

Figure 1 is a perspective view of a trim piece having a double deployment door formed as a part of the process of the present invention, the trim piece being preweakened by laser beam apparatus depicted diagrammatically.

Figure 2 is a perspective view of a single door substrate panel formed as a part of the process of the present invention.

Figure 3 is a perspective view of a single door substrate panel formed as a part of the process according to the present invention, having a hinge reinforcement added.

Figure 4 is a perspective view of a trim piece formed by the process according to the present invention.

Figure 5 is a view of the section 5-5 taken in Figure 4.

Figure 6 is a view of the section 6-6 taken in Figure 4.

Figure 7 is a view of the section taken through a trim piece having an alternate form of the tab features.

Figure 8 is a sectional view showing an alternate form of preweakening of the covering layers.

Detailed Description

[0015] In the following detailed description, certain specific terminology will be employed for the sake of clarity and a particular embodiment described in accordance with the requirements of 35 USC 112, but it is to

be understood that the same is not intended to be limiting and should not be so construed inasmuch as the invention is capable of taking many forms and variations within the scope of the appended claims.

[0016] Referring to the Drawings, Figure 1 shows the inside of a trim piece 10 comprised of a substrate panel 12 which provides the structural integrity of the trim piece 10, and hence is thick enough to be relatively rigid.

[0017] The substrate panel 12 can be constructed using conventional materials such as suitable polymers or wood fiber, and using conventional processes such as injection molding, casting, and thermoforming.

[0018] In the embodiment shown in Figure 1, a deployment opening is defined by a pair of generally rectangular deployment door panels 14 integrally connected along one of the sides 16, each defining a parallel hinge axis for swing out movement of the door panels 14.

[0019] The perimeter of the other three sides of the door panels 14 are defined by a gap pattern 18 which may be preformed at the same time as the substrate panel 12 itself.

[0020] The substrate panel 12 has one or more covering layers 20 which overlie the exterior of the substrate panel 12, i.e., the side of the trim piece 10 exposed to view within the passenger compartment. The covering layer 20 may be a flexible skin of a plastic such as TPO and may be supported by a foam layer 22. The covering layers 20, 22 extend smoothly over the door panels 14 and the gap 18 to render the door panels 14 not visible to a passenger or driver within a vehicle passenger compartment. The substrate panel is generally attached to a rigid supporting structure in the vehicle.

[0021] The inside of the cover layers 20, 22 are exposed within the perimeter gap 18 so as to allow a preweakening cut 19 to be applied after the trim piece has been completed to eliminate the need to align a preweakened cover layers 20, 22 with the door panels 14.

[0022] Such preweakening is preferably carried out with a laser beam, as described in detail in U.S. patents 5,744,776 and 5,883,356, issued to the same assignee as the assignee of the present application. Other processes may also be used, such as a mechanical knife (as described in U.S. patent 5,217,244, also assigned to the assignee of the present application).

[0023] Ultrasonic, hot knife, and water jet machining are other processes which may be used.

[0024] A laser beam generator 26 is shown in Figure 1, with positioning apparatus 24 provided to cause the laser beam to trace along the gap 18 so as to cause continuous or intermittent scoring of the covering layers 20, 22 to accomplish a preweakening as described in the above referenced patents. A gauging sensor (not shown) may also be used to carry out a particular preweakening program, and laser generator controller 28 may vary the laser power, velocity, etc. to in turn vary the depth or extent of scoring or cutting to achieve a

desired degree of preweakening along the gap pattern 18.

[0025] As also shown in Figure 1, bridging tabs 30 may extend across the gap 18 at selected locations to provide strength to the trim piece 10 by connecting the door panels 14A, 14B to each other and to the adjacent regions of the substrate panel 14.

[0026] Figure 2 shows the application to a substrate panel 12A having only a single deployment door panel 32. Also shown is a stiffener frame 34 affixed to the perimeter of the gap 18A and door panel 32 to stiffen the substrate panel 12A for purposes as described in U.S. patent 5,393,088.

[0027] Figure 3 shows the addition of a hinge reinforcement 36, such as a sheet of scrim, which can be attached to insure that the door panel 30 does not break free. An integrally molded reinforcement may also be employed. Such a reinforcement could also be extended to cover the complete door panel.

[0028] Figures 4-8 show further details of the trim piece 10 made by the process of the present invention.

[0029] The covering layers may comprise a polymeric, leather or fabric skin 20 and foam plastic layer 22 overlying the substrate 12.

[0030] The tabs 30 can take various design configurations and extend across the gap 18. The tabs can be integrally molded with the substrate or can be attached to the substrate separately as shown in Figure 7. The hinge 16 may comprise a reduced cross section area recessed in from either surface of the substrate panel 12A.

[0031] The weakening cut or cuts 19 are aligned with the gap 18 and may only penetrate the foam layer 22 (Figure 6) or a cut 19A may extend into the skin 20 (Figure 8).

[0032] Figure 7 shows a tab 30A which is not integral but rather underlies the door panel 14 to provide support against inward pushing forces applied to the outside of the trim piece 10.

[0033] Forming of the substrate panel can be done in several ways including injection molding, casting or thermoforming. Preferred materials for the substrate panel comprise thermoset and thermoplastic polymers but other materials can be used, including wood fiber and metal. An air bag canister can also be included as an integral part of the substrate panel. The door panel or panels can be made integrally with the substrate panel (i.e., door and substrate molded simultaneously into one piece) or made separately (i.e., substrate panel molded with door opening and door panel attached to substrate panel subsequently). The door panel or panels and particularly the hinge can be further reinforced via rigid or flexible materials (hard plastic scrim fabric, metal, etc.). This reinforcement can take place either during any forming of the substrate panel, i.e., by co-molding scrim fabric with integral deployment door hinge, or after forming of the substrate door panel. The gap separation between the door panel sides and the

substrate panel can be complete with no material joining the two panels or partial. The optional stiffener frame either integral with the substrate panel or separate may also be located extending outside and around the door opening perimeter. Alternatively, the substrate panel may be attached to the air bag canister through fasteners or bolts located around the door perimeter.

[0034] The covering layers can be flexible or rigid and include foams, leather, vinyl/TPO/TPE/TPU skins, fabrics and laminated wood. In a foam/skin/construction, injection of plastic foam between the skin and substrate layers generally requires that the door perimeter gap be temporarily sealed to allow proper foam expansion. Preweakening of one or more of the covering layers can be carried out by any of several contacting or non-contacting scoring-cutting techniques, i.e., mechanical knife, water jet, ultrasonic cutting, etc. A preferred method is cutting or scoring with a laser beam that can pre-weaken rapidly, accurately and in any desirable configuration and pattern, i.e., continuous or semi-continuous grooves, perforations, slots, etc. The preweakening scoring or cutting can be carried out from either side of the substrate panel but preferably from the inside.

[0035] If a laser beam is utilized, this enables the trim piece manufacturer to first assemble the trim piece and then rapidly and accurately pre-weaken the covering layers through or along the separation between the substrate panel and the door panel or panels without having to cut through the substrate panel, which can be of substantial thickness.

[0036] During the preweakening step, gauging of the thickness of the covering layer or layers thickness can be included to better control the laser so that it removes the desired amount of covering material. Gauging can be done from either side of the covering layer or layers using any of various types of sensors, including ultrasonic, infrared, and capacitance type sensors.

Claims

1. A process for constructing a trim piece having a section preweakened in a pattern to allow formation of one or more deployment doors for an air bag installation to be overlain by said trim piece preweakened section, the process comprising the steps of:

forming a stiff substrate panel with one or more door panels recessed into said substrate panel, with a gap pattern extending about a portion of the perimeter of said one or more door panels, said gap extending completely through said one or more door panels,

said forming step including the step of forming said one or more door panels so as to be joined along one side to said substrate panel to form a hinge;

thereafter overlaying said substrate panel and

said one or more door panels with one or more cover layers extending across said substrate panel and said one or more door panels to bridge said gap pattern; and subsequently preweakening at least one of said overlaying one or more covering layers by cutting into the inside of said cover layers through said gap.

2. The process according to claim 1 further including the step of partially preweakening said one or more cover layers along said gap.
3. The process according to claim 1 or 2 further including the step of integrally forming one or more bridging tabs extending across said gap to join said one or more door panels to adjacent portions of said substrate panel.
4. The process according to anyone of the foregoing claims further including the step of reinforcing the perimeter of said opening with a stiffener frame.
5. The process according to anyone of the foregoing claims further including the step of reinforcing said hinge of said one or more door panels.
6. The process according to anyone of the foregoing claims further including the step of reinforcing said one or more door panels.
7. A process for constructing a trim piece having a section preweakened in a pattern to allow formation of one or more deployment doors for an air bag installation to be overlain by said trim piece preweakened section, the process comprising the steps of:

forming a stiff substrate panel having an opening therein; recessing one or more door panels into said opening, with a predetermined gap between adjacent portions of said one or more door panels and the perimeter of said opening; said one or more door panels joined along one side to said substrate panel to form a hinge; overlaying said substrate panel with one or more cover layers extending across said one or more door panels and said gap therebetween; preweakening said overlaying covering layers by scoring portions of the inside of said cover layers at least partially along said gap.

8. A process for constructing a trim piece having a section preweakened in a pattern to allow formation of two deployment doors for an air bag installation to be overlain by said trim piece preweakened section, the process comprising the steps of:

forming a stiff substrate panel;
recessing two door panels into an opening in
said substrate panel, with a gap between adja-
cent portions of said door panels, said gap ex-
tending completely through said door panels;
said recessing step including the step of form-
ing each of said two door panels so as to be
joined along one respective side thereof to an
adjacent portion of said substrate panel to form
a hinge;
thereafter overlaying said substrate panel and
said recessed door panels with one or more
cover layers extending across said substrate
panel and said door panels to bridge said gap
therebetween; and
subsequently preweakening at least one of said
overlaying one or more covering layers by cut-
ting into the inside of said cover layers through
said gap between said doors.

5

10

15

20

9. The process for constructing a trim piece having a
section preweakened in a pattern to allow formation
of a pair of deployment doors for an air bag instal-
ment to be overlain by said trim piece preweakened
section, the process comprising the steps of:

25

forming a stiff substrate panel having an open-
ing therein; recessing a pair of door panels into
said opening, with a predetermined gap be-
tween adjacent portions of said door panels,
each of said door panels joined along one side
to said substrate panel to form a hinge;
overlaying said substrate panel with one or
more cover layers extending across said door
panels and said gap therebetween;
preweakening said overlaying covering layers
by scoring portions of the inside of said cover
layers at least partially along said gap.

30



35



40

45

50

55








FIG-5




FIG-6




FIG-7




FIG-8



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 03 01 4875

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 5 738 367 A (BAUER JR LEGAL REPRESENTATIVE ET AL) 14 April 1998 (1998-04-14) * column 2, line 1 - line 49 * * column 3, line 43 - line 67; figures *	1-9	B29C59/00 B60R21/20
X	US 5 131 678 A (RHODES JR RICHARD D ET AL) 21 July 1992 (1992-07-21) * column 3, line 37 - line 47; figure 5 *	1,2,7	
A	US 5 484 561 A (WEBER JOHN C ET AL) 16 January 1996 (1996-01-16) * column 2, line 2 - line 32; figures 3,4 *	1,2,7-9	
A	US 5 728 342 A (WIRT W GARY ET AL) 17 March 1998 (1998-03-17) * column 3, line 48 - column 6, line 39; figure 4 *	1,2,6,7	
A	US 5 744 776 A (BAUER DAVID J) 28 April 1998 (1998-04-28) * the whole document *	1,2,7-9	TECHNICAL FIELDS SEARCHED (Int.Cl.7)
A	US 5 501 890 A (MILLS DANIEL H) 26 March 1996 (1996-03-26) * figures 6,7 *	1,2,7-9	B60R B29C
A	US 5 375 876 A (DISALVO ANTHONY J ET AL) 27 December 1994 (1994-12-27) * figures 1,2 *	1,7-9	
A	US 5 395 668 A (ANDO HIKARU ET AL) 7 March 1995 (1995-03-07) * column 3, line 6 - line 10; figure 1 *	5	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 24 September 2003	Examiner Fageot, P
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 02 (P04C01)

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 03 01 4875

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

24-09-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5738367	A	14-04-1998	NONE
US 5131678	A	21-07-1992	CA 2056291 A1 04-06-1992 DE 69118201 D1 25-04-1996 DE 69118201 T2 31-10-1996 EP 0559766 A1 15-09-1993 ES 2084994 T3 16-05-1996 JP 6504503 T 26-05-1994 JP 3411569 B2 03-06-2003 KR 211712 B1 02-08-1999 MX 9102323 A1 01-06-1992 WO 9209458 A1 11-06-1992
US 5484561	A	16-01-1996	NONE
US 5728342	A	17-03-1998	EP 0714817 A2 05-06-1996 JP 8207687 A 13-08-1996 US 5533748 A 09-07-1996
US 5744776	A	28-04-1998	US 5375875 A 27-12-1994 US 5217244 A 08-06-1993 CA 2145450 A1 01-05-1996 DE 29522423 U1 18-06-2003 DE 69517918 D1 17-08-2000 DE 69517918 T2 18-01-2001 DE 711627 T1 30-12-1999 EP 0711627 A2 15-05-1996 EP 0963806 A1 15-12-1999 JP 8282420 A 29-10-1996 US 6294124 B1 25-09-2001 US 2003107203 A1 12-06-2003 US 6267918 B1 31-07-2001 US 2001010423 A1 02-08-2001 CA 2133534 A1 06-04-1995 EP 0648647 A1 19-04-1995 JP 7164991 A 27-06-1995 US 2003155749 A1 21-08-2003 US 5797619 A 25-08-1998 CA 2021117 A1 15-01-1991 DE 69013778 D1 08-12-1994 DE 69013778 T2 08-06-1995 DE 69032030 D1 12-03-1998 DE 69032030 T2 02-07-1998 EP 0408064 A1 16-01-1991 EP 0595374 A1 04-05-1994 JP 3128821 B2 29-01-2001

EPO FORM P0469

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 01 4875

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

24-09-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5744776 A		JP 3295736 A	26-12-1991
US 5501890 A	26-03-1996	US 5443777 A	22-08-1995
US 5375876 A	27-12-1994	CA 2133532 A1	06-04-1995
		EP 0648648 A1	19-04-1995
		JP 7164993 A	27-06-1995
US 5395668 A	07-03-1995	JP 4110117 A	10-04-1992
		JP 7067711 B	26-07-1995
		JP 3168646 B2	21-05-2001
		JP 5162603 A	29-06-1993
		DE 69109780 D1	22-06-1995
		DE 69109780 T2	15-02-1996
		EP 0475198 A2	18-03-1992

EPO FORM P4439

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

THIS PAGE BLANK (USPTO)